

## **COREFIL 100R**

Flux cored wires [FCAW]

Construction, unalloyed steels

CLASSIFICATION:	APPROVALS:	APPLICATION:
EN ISO 17632-A : T 46 2 PM (C) 1 H5 AWS A-5.20 : E 71T-1M(C)/9M(C)	CE	Power generation industry Constructions & Engineering Metallurgy (Steelworks) Mining Petrochemical and chemical industry Shipbuilding&Offshore

- Rutile flux cored wire with fast freezing slag.
- Designed for manual or automatic welding.
  For welding in all positions with CO2 and M21 gas shielding.
- Very good and easy operated in all positions, excellent weld formation.
- Very good root pass on ceramic backing
  Possibility to perform welds in PF without waving the material.
- Works with a spray arc.
- Forced welding at low voltages (24-25 V) with a feed of 10-11 m and more.
- High purity of radiographic and ultrasonic tests.
- Low hydrogen content (H<5ml/100g).

Base material		
	EN	
Construction steels:	S185, S235, S275, S355 e.t.c.	
Shipbuilding steels:	Grade A, B, D, AH32-DH36 e.t.c.	
Casts:	GP240R e.t.c.	
Pipe steels:	L210, L240, L290, L360	
	L240MB, L290MB, L360MB, L360QB, L240MB	
	L290MB, L360MB, L415MB, L415NB	
	X42, X46, X52, X60	
	P235T1, P235T2, P275T1	
	P275T2, P355N	
	e.t.c.	
Tanks and pressure steels:	P235GH, P265GH, P295GH, P355GH	
Finegrained steels:	S275, S355, S420	
	S275M, S275ML, S355M, S355ML, S420M, S420ML	
	e.t.c.	

## **Typical chemical composition %**

<b>C</b> < 0,06	<b>Si</b> < 0,60	<b>Mn</b> 1,50	<b>P</b> < 0,02	<b>S</b> < 0,02		
Typical mechanical properties						
Yield stren	gth Re [N	/mm2]	> 460			
Tensile str	ength Rm	[N/mm2]	530 - 6	80		
Elongation	A5 [%]		> 25			

Impact energy Kv [J]	>47 (-20°C), typ	>47 (-20°C), typical 150J / > 47 (-30°C), typical 130J /					
Wire/rod type	rutile cored						
Hydrogen content	< 5ml/100g						
Welding current	= +						
Welding positions							
Shielding gases acc. to EN ISO         C1 - 100% CO2 / M21 - Ar + 15 - 25% CO2 /           14175         C1 - 100% CO2 / M21 - Ar + 15 - 25% CO2 /							
Welding parameters and packing							
ø 1,2	Welding current [A] 160-280	<b>Gas flow</b> 12-18	Weight of packet [kg] 15,0				
METALWELD-FIPROM POLSKA spółka z o.o.							
ul. Mikołajczyka 57, 41-200 Sosnowiec							
+48 (32) 297 75 50 - 51							
+48 (32) 297 75 88							
export@metalweld.pl							