

# TIGWELD 253MA

TIG Rods [GTAW]

Stainless and high alloyed steels

<b>CLASSIFICATION:</b> EN ISO 14343-A : W 21 10 N W.Nr. : 1.4835	<b>APPROVALS:</b>	<b>APPLICATION:</b> Power generation industry Metallurgy (Steelworks) Petrochemical and chemical industry
--	-------------------	--

- Austenitic chromium-nickel wire with the addition of nitrogen and cerium, intended for welding steels operating at high temperatures, exposed to high corrosion.
- It shows excellent resistance to high temperatures (the most suitable temperature range is 850 - 1100 °C), high creep strength, very good resistance to isothermal and especially cyclic oxidation.
- Not suitable for applications exposed to wet corrosion.
- Prior to welding, thorough brushing or grinding of carbon plates and previous weld seams is recommended.

## Base material

Outokumpu	SS	ASTM/UNS	W.Nr.	EN 10095	UGINE
153MA	2372	S30415	1.4818		
263MA	2368	S30815	1.4835	X9 CrNiSiNce21 11 2	
			1.4828	X15CrNiSi20-1 2	Uginox R 2012
			1.4829	X12 CrNi22-12	
253MA		S30815	1.4893	X8CrNiSiN21-1 1	

## Typical chemical composition %

C	Si	Mn	Cr	Ni	Mo	N
0,07	1,50	0,40	21,00	10,00	0,10	0,16

## Typical mechanical properties

<b>Yield strength Re [N/mm<sup>2</sup>]</b>	≥ 350
<b>Tensile strength Rm [N/mm<sup>2</sup>]</b>	≥ 550
<b>Elongation A5 [%]</b>	≥ 30
<b>Impact energy Kv [J]</b>	~ 130(20°C) /

**Welding positions**



**Shielding gases acc. to EN ISO 14175** I1 - Ar / I3 - Ar + >0-95% He /

## Welding parameters and packing

∅	Length [mm]	Weight of carton [kg]
1,6	1000 /	5.0
2,0	1000 /	5.0
2,4	1000 /	5.0

**METALWELD-FIPROM POLSKA spółka z o.o.**

ul. Mikołajczyka 57, 41-200 Sosnowiec

+48 (32) 297 75 50 - 51

+48 (32) 297 75 88

[export@metalweld.pl](mailto:export@metalweld.pl)