

SAWELD NiCu1

Submerged arc welding wires [SAW]

Low alloyed steel

CLASSIFICATION: EN ISO 14171-A : S2NiCu1 AWS A-5.23 : EG W.Nr. : 1.5425	APPROVALS:	APPLICATION: Constructions & Engineering Steel construction yards Automobile		
<ul style="list-style-type: none">• Submerged arc welding wire for weathering steels• Good resistance to atmospheric corrosion				
Application				
For welding weathering steels				
Typical chemical composition %				
C 0,10	Si 0,25	Mn 1,00	Ni 0,85	Cu 0,47
Typical mechanical properties				
Wire/rod type		submerged arc welding		
METALWELD-FIPROM POLSKA spółka z o.o. ul. Mikołajczyka 57, 41-200 Sosnowiec +48 (32) 297 75 50 - 51 +48 (32) 297 75 88 export@metalweld.pl				