

## BASOWELD 55

Electrodes MMA [SMAW]

Construction, unalloyed steels

CLASSIFICATION:	APPROVALS:	APPLICATION:
EN ISO 2560-A : E 46 6 B 31 H5 DIN 8529 : EY 46 76 MnB AWS A-5.1 : E 7018-1	UDT	Power generation industry Constructions & Engineering Metallurgy (Steelworks) Mining Shipbuilding&Offshore
<ul style="list-style-type: none"> <li>• Basic coated, low hydrogen.</li> <li>• Recommended for welding steels with tensile strength up to 680 MPa, working in extremely low temperature, in -60°C.</li> <li>• Especially recommended for welding construction steels dynamically loaded.</li> </ul>		



### Base material

	EN
Construction steels:	S235-S355
Boiler plates:	P235GH-P355GH
Pipe steels:	P235-P355N
Shipbuilding plates:	A, B, D, E, AH32-EH36
Finegrained steels:	S275-S420, S460

### Typical chemical composition %

C	Si	Mn
0,07	0,30	1,50

### Typical mechanical properties

<b>Yield strength Re [N/mm<sup>2</sup>]</b>	>460
<b>Tensile strength Rm [N/mm<sup>2</sup>]</b>	530-680
<b>Elongation A5 [%]</b>	>20
<b>Impact energy Kv [J]</b>	>47J (-60°C) /
<b>Coating type</b>	basic
<b>Hydrogen content</b>	<5 ml/100 g
<b>Welding current</b>	
<b>Welding positions</b>	
<b>Redrying</b>	300 - 350°C / 2 h

### Welding parameters and packing

∅	Length [mm]	Welding current [A]	Weight of packet [kg]	Weight of carton [kg]	Pcs/1 kg
2,5	350 /	65-90	4,0	12,0	44
3,2	350 / 450 /	110-140	4,0/5,5	12,0/16,5	20

4,0	450 /	140-180	5,5	16,5	14
5,0	450 /	180-230	5,5	16,5	9

**METALWELD-FIPROM POLSKA spółka z o.o.**

ul. Mikołajczyka 57, 41-200 Sosnowiec

+48 (32) 297 75 50 - 51

+48 (32) 297 75 88

export@metalweld.pl