

## UTOPWELD 38

Electrodes MMA [SMAW]

Hardfacing and repairing

<b>CLASSIFICATION:</b>	<b>APPROVALS:</b>	<b>APPLICATION:</b>
EN ISO 14700-A : E Fe3 DIN 8555 : E 3-UM-40-PT	UDT	Hardfacing and repairing

- Basic electrode with additions of Mo, Cr and V.
- High resistance to tensile strength, abrasion, impact.
- The weld metal is easily machined.
- Deposited weld is resistant to metal-to-metal wear.
- Recommended for hardfacing hot and cold working tools and for filling cavities.
- For operation at high temperatures: > 900°C.

### Application

Die plates, dies and containers, presses for extrusion of metal pipes and rods; for the manufacture of shafts, screws, nuts, rivets and pins, casting dies, die inserts and others. Regeneration of teeth in gears.

### Base material

Tool steels

### Typical chemical composition %


<b>C</b>	<b>Cr</b>	<b>Mo</b>	<b>V</b>	<b>W</b>
0,13	5,00	4,00	0,20	+

### Typical mechanical properties

**Hardness** 36 - 42 HRC / The hardness of the overlay depends on the relevant welding conditions, the number of layers and the chemical composition of the base material. /

**Coating type** basic

**Welding current**



**Welding positions**



**Redrying** 400°C / 1 h

**Additional description** Recommended preheating 300-500°C

### Welding parameters and packing

∅	Length [mm]	Welding current [A]	Weight of packet [kg]	Weight of carton [kg]	Pcs/1 kg
2,5	350 /	70-90	4,0	12,0	57
3,2	350 /	110-135	4,4	13,2	28
4,0	450 /	130-170	5,4	16,2	14
5,0	450 /	180-220	5,5	16,5	6

**METALWELD-FIPROM POLSKA spółka z o.o.**

ul. Mikołajczyka 57, 41-200 Sosnowiec

+48 (32) 297 75 50 - 51

+48 (32) 297 75 88

[export@metalweld.pl](mailto:export@metalweld.pl)