

SAWELD 3

Submerged arc welding wires [SAW]

Low alloyed steel

CLASSIFICATION: EN ISO 14171-A : S3 AWS A-5.23 : EH10K W.Nr. : 1.0496	APPROVALS:	APPLICATION: Constructions & Engineering Shipbuilding&Offshore
<ul style="list-style-type: none">• Submerged arc welding wire for structural steels with plasticity up to 420MPa.• Recommended in shipbuilding, industrial construction, etc.		
Typical chemical composition %		
C 0,10	Si 0,10	Mn 1,55
Typical mechanical properties		
Wire/rod type	subrmerged arc welding	
METALWELD-FIPROM POLSKA spółka z o.o. ul. Mikołajczyka 57, 41-200 Sosnowiec +48 (32) 297 75 50 - 51 +48 (32) 297 75 88 export@metalweld.pl		