

## SAWELD CrMo1

Submerged arc welding wires [SAW]

Creep resistant steels

CLASSIFICATION:	APPROVALS:	APPLICATION:
EN ISO 24598-A : S CrMo1 AWS A-5.23 : EB2R W.Nr. : 1.7346		Power generation industry

- Submerged arc welding wire for 1.25% Cr and 0.5% Mo steel.
- Weld working temperature up to 550°C.
- Low Bruscano ratio: approximately X13 ppm.

### Application

For welding creep-resistant steels, such as: steam boilers, pipelines and fittings, working under pressure and at elevated temperatures, and for repairing thermal energy devices. Also used in the petrochemical industry.

### Typical chemical composition %

C	Si	Mn	Cr	Mo
0,10	0,15	0,95	1,20	0,50

### Typical mechanical properties

**Yield strength Re [N/mm<sup>2</sup>]** >470

**Tensile strength Rm [N/mm<sup>2</sup>]** >550

**Elongation A5 [%]** >20

**Wire/rod type** subrmerged arc welding

### METALWELD-FIPROM POLSKA spółka z o.o.

ul. Mikołajczyka 57, 41-200 Sosnowiec

+48 (32) 297 75 50 - 51

+48 (32) 297 75 88

export@metalweld.pl